



DATA SHEET
NYACOL® LiSol™ 6

LiSol™ 6

Lithium Stabilized Colloidal Silica

NYACOL LiSol™ 6 is a lithium stabilized colloidal silica intended for use in treating concrete. The small particle silica acts to increase the density and hardness of concrete surfaces and lithium acts to reduce the effects of alkali-silica reaction or ASR. ASR effects include abnormal expansion and cracking of concrete. LiSol 6 is environmentally friendly. The pH is moderate compared to lithium silicate and there is no nitrate or chloride in the product.

TYPICAL PROPERTIES

Appearance:	Clear liquid
Solids, % by weight:	13 - 15
Particle Size, nm	4 - 6
Viscosity, cP:	<10
pH:	9 - 10
% Li:	0.5

PRIMARY APPLICATIONS

LiSol 6 can be used on exterior concrete and warehouse floors, commercial floors, and large scale construction. The product provides a dense surface with improved wear resistance and reduced dusting and protection from ASR induced expansion and cracking. Coverage is 400-500 square feet per gallon.

METHOD OF APPLICATION

New concrete: Dilute 6 to 1 with water and use a low-pressure sprayer. The surface should be fully wetted and then allowed to dry.

Existing concrete: The surface should be scrubbed clean. Dilute 4 to 1 with water and use a low-pressure sprayer to wet the surface. Allow 1-2 hours drying time.

A water repellent coating after coating with LiSol 6 will further improve the performance against ASR. Consult Nyacol for recommendations.

PACKAGING

LiSol 6 is available in 5-gallon pails and 55-gallon drums.

STORAGE

LiSol 6 should be stored at normal warehouse conditions.

SAFETY

A Safety Data Sheet for LiSol 6 will be supplied on request.

FOR ADDITIONAL INFORMATION OR TO PLACE AN ORDER

Nyacol Nano Technologies, Inc.
P.O. Box 349
Megunko Road
Ashland, MA 01721-0349 U.S.A.

Telephone: 800-438-7657 Toll-Free
508-881-2220 Local Area
Fax: 508-881-1855
Internet: www.nyacol.com

Information herein is accurate to the best of our knowledge. Suggestions are made without warranty or guarantee of results. Before using, user should determine the suitability of the product for its intended use and user assumes the risk and liability in connection therewith. We do not suggest violation of any existing patents or give permission to practice any patented invention without a license. 20140403

NYACOL is a trademark of Nyacol Nano Technologies, Inc.
P.O. Box 349, Ashland, MA 01721-0349 USA Tel.: 508-881-2220